

Metal corrosion in wood joint products and structures: a review

A. Wahyudianto,¹* A. Fernandes,^{2,3} Erwin⁴ and Wajilan¹

¹Politeknik Negeri Samarinda, Jl. DR Ciptomangunkusumo, Kampus Gunung Lipan, Samarinda, East Kalimantan, Indonesia

²Research Center for Biomass and Bioproducts, National Research and Innovation Agency, Jl. Raya Jakarta- Bogor Km. 46, Cibinong, Kab. Bogor, West Java, 16911, Indonesia

³Master Student at Forestry Faculty, Mulawarman University, Jl. Penajam, PO.BOX. 1013, Samarinda, East Kalimantan, Indonesia

⁴Forestry Faculty, Mulawarman University, Jl. Penajam, PO.BOX. 1013, Samarinda, East Kalimantan, Indonesia

*E-mail: arif.wahyudianto@polnes.ac.id

Abstract

Nails and screws are relatively small parts connecting wood items into construction products ranging from simple ones, such as a drawer, to large structures, such as houses and bridges. Metal nails and screws will corrode both outside and inside the wood. The wood around the nail or bolt will also deteriorate. Metal corrosion and wood deterioration are the basis for researchers to publish the corrosion rate of nails and screws, the composition of metal elements, and wood extractives that affect the corrosion rate. These publications need to be compiled into a review to obtain a complete set of various perspectives concerning nail and screw corrosion in wood. The chemical elements of nails and bolts, such as iron, carbon, zinc, and other chemical elements, play an important role. The wood extractives that comprise phenolic compounds, organic acids, and other wood chemical compounds affect the corrosion rate. The occurrence of corrosion processes and interactions with wood cause damage to wood and wood deterioration that can cause damage to wooden structures. Prevention of corrosion and wood damage can be done by coating nails and bolts and improving the quality of wood. This step will result in a wooden structure connected using nails and screws over a long period for human safety and conserving wood-producing trees in the nature.

Received: May 10, 2022. Published: August 25, 2022

doi: [10.17675/2305-6894-2022-11-3-21](https://doi.org/10.17675/2305-6894-2022-11-3-21)

Keywords: *nails, screws, wood deterioration, corrosion.*

1. Introduction

Citizens in various countries still choose wood as a structural and building material because it has multiple advantages [1]. Wood is a renewable resource that is widely used in construction and buildings [2]. Wood also has high mechanical properties and great thermal insulation [3]. Wooden houses account for 50% of extracted materials, 35% of total

greenhouse gas emissions, 42% of total energy consumption, and 30% of water consumption [4].

While metals require more complicated processes to be used in construction and buildings [5], they are used as complementary material in the form of construction connectors in wooden structures. Metal as a fastener in a wood construction must be able to support the wooden structure [6]. Egyptians used nails for wooden materials starting from 3400 BC [7], while screws were patented in 1902 [8].

Metal corrosion can occur due to direct contact of a metal with water and the effect of air humidity around the metal [9]. Metal corrosion in wood is very specific because various factors affect corrosion in wood, for example, wood moisture content, extractives and additives [10].

Corrosion of metal connections in wood has been widely published. There is a significant gap in research on the deterioration of wood affected by metal corrosion of wood joints [11]. Therefore, it is necessary to study metal corrosion and the resulting wood damage to get an idea of its application in the field of wood structures in the present and in the future.

2. Wood as outdoor constructions

Outdoor round timber constructions include playground equipment, pedestrian and non-pedestrian bridges, and watchtowers [12]. Outdoor constructions from sawn timber include houses, buildings, docks, bridges, and others. Wooden houses provide comfortable atmosphere in the house [3] and tend to be lightweight and resistant to earthquakes [2]. Wooden houses give the foremost common, practical, and economical arrangement for development [13]. People can build wooden houses from sawn timber and wood-derived products such as Laminated Veneer Lumber (LVL), Cross Laminated Timber (CLT), and Glued Laminated Timber (GLT).

Today, wooden houses in Indonesia are still found in various forms and names. Wooden houses in Java are known as Joglo [14], Batak Karo wooden houses in North Sumatra are known as Siwaluh Jabu [15], and several types of wooden houses in other areas. In Kalimantan, the wooden house of the Dayak Bidayuh is known as Baruk [16], and the wooden house of the Dayak Ngaju is known as Betang [17]. An example of a wooden house in Kalimantan can be seen in the following picture.

One of outdoor wood constructions commonly found in East Kalimantan is a wooden tower that supports a water tank above it. The metal bolts on the wooden tower significantly contribute to its construction strength [18].

Bridges can be made of wood at a lower cost [19]. The bridge construction has a wooden foundation that is connected to the ground [20] and there are parts that become the base for vehicles that pass through it. To connect parts together, one should use screws because there is a dynamic load that causes the connection to loosen. When the connection becomes loose, the screw can be re-tightened.



Figure 1. Wooden house in Samarinda, East Kalimantan. The wooden walls are nailed, and the support poles are screwed.

Outdoor wood constructions tend to be larger, thus requiring more joints. The higher the specific gravity of the wood, the more bolts that need to be attached to the wooden construction [21].

Beside permanent buildings, there are temporary constructions using Gelam (*Melaleuca cajuputi*) wood [22, 23]. Gelam wood structures are arranged when helping workers to cast or construct buildings and to reach higher locations. Nails are used for connecting Gelam wood because they are more practical to use [24].

3. Wood as indoor constructions

Indoor wooden constructions tend to be smaller with lighter loads. Various indoor furniture is made of wood, such as tables, chairs, cabinets, and others. Door connections in the cabinets use bolts [25]. The drawer runners are connected to the cabinet walls using bolts [26].

Indoor wood constructions are not only made of solid wood but also use other processed wood products such as plywood [27] and expansion of MDF [28]. Wood construction materials affect the type of connection used, for example, plywood and MDF tend to use screw connections, while solid wood tends to use nails. On plywood and MDF, the type of adhesive will determine the corrosion rate at the joint [29]. Phenol-formaldehyde besides being useful as an adhesive also functions as an anti-corrosion coating [30].

4. Metal as wood constructions connector

Screwed joints have lower quality and solidness than nailed joints [31]. The wood is drilled beforehand so the bolts can be screwed fixedly to the wood and minimize the wood damage [32]. Screws are used for the connection of large parts of wood and various other wood-derived products, such as CLT expansion [33]. Based on various types of screws, stainless

steel has good corrosion resistance as screws on wood but tends to be easily detached when used [34]. Screw installation in the radial direction on the CLT has a higher strength than the tangential direction [35]. The installation of several bolts on wooden joints requires a certain distance to obtain maximum strength [36].

Nails are used widely and traditionally on small-sized wood items [33]. Nails can be attached directly to wood, or the wood pre-drilled and then nailed using a larger diameter than the drill hole [37]. The nailed joints appear way better bendable and scattering than screwed joints [31]. Nails can connect a beam-column with high strength mechanical performance [38]. CLT is an innovative panel product joined by nails together for lightweight structures [39]. Nails not only join several wood panels together but can also prevent wood densification swelling [7].

5. Effect of metal chemical elements on metal corrosion rate

Bolts with iron (Fe) as the main component have the disadvantage of being easily corrodible [40], so they are made of metal alloys with chemical elements such as molybdenum (Mo), silicon (Si), and cadmium (Cd) as coating materials [41]. Bolts with 8–16 mm diameter contain aluminum (Al), steel (Stl), bronze (Brz), cast iron (CI), copper (Cu) and brass (Br) [42]. Aluminum alloy screw AA130 is made of 0.157 Fe, 0.058 Si, 0.022 Zn, 0.013 Cu, 0.006 V, 0.004 Ni, 0.002 Ti, 0.001 Mn, and 99.1 Al [43]. Combinations of aluminum (Al), chrome (Cr), and zinc (Zn) were detected in bolts [44]. Electroplated galvanized screw corrosion rate is up to 60 $\mu\text{m}/\text{year}$ [29].

Iron (Fe), tin (Sn), silver (Cu), lead (Pb), arsenic (As), silver (Ag), antimony (Sb) elements were detected in aged bronze nails [45]. Nail corrosion rate ranges from 0.042–0.171 mpy [46]. Nail corrosion rate depends on the constituent material: the average corrosion rate of carbon steel nails is 45 $\mu\text{m}/\text{year}$, that of 5056 aluminum nails is 20 $\mu\text{m}/\text{year}$, and that of hot-dip galvanized nails is 75 $\mu\text{m}/\text{year}$ [29].

The zinc element in the metal will corrode first to protect the iron element from being corroded [47]. The higher the carbon element in the metal, the higher the corrosion rate in the metal [48]. A small nickel concentration in steel screw can reduce the corrosion rate [49]. The presence of the Cr element is stronger as inhibiting metal corrosion rate than the Sn element [50].

6. Effect of wood chemical components on the metal corrosion rate

The content of natural acids within the wood of tree species ranges within 0.21–1.08% [51]. The type of wood determines its extractive acidity. Elm (*Ulmus*) wood is an example of wood that has extractives that are weakly acidic, while oak (*Quercus*) wood has extractives that are acidic and corrosive [52]. Organisms that live on wood, such as stain molds, affect the extractive acidity of wood. Molds (*Aspergillus niger*, *A. flavus*, *Alternaria tenuissima*, *Fusarium culmorum*, and *Trichoderma harzianum*) have various concentrations of organic acids (oxalic, citric, tartaric, succinic, glutaric, acetic, propionic, and butyric) in

the wood extractives [53]. The lower the pH of the wood, the faster the metal corrosion rate in the wood connection [54].

Wood extractives may contain fatty acids such as heptadecanoic acid, which are lipophilic [55]. Fatty acids are formed when trees grow and can be stored in wood for a long time [56]. Fatty acid groups such as sterols, lipopeptides, lactones, amides and pyrroles function as antifouling agents on metal surfaces to prevent metal corrosion [57].

Wood extractives contain some phenolic compounds such as tannins, quinones, flavonoids, terpenoids, and alkaloids [58]. Quinones such as 2-amino-4-[4-(dimethylamino)phenyl]-7-hydroxy-1,4-dihydroquinoline-3-carbonitrile function as a corrosion inhibitors on mild steel under acidic conditions through a cathodic inhibition mechanism [59]. Myricetin and rutin are flavonoids that function as corrosion inhibitors on mild steel and aluminum in 2 M HCl solutions [60].

Tannins are chemical compounds containing polyphenols that are non-toxic and can be degraded naturally [61]. Tannins from tropical woods are dominated by catechin species, while gallic species dominate those from sub-tropical areas [62]. The wood contains 0.83–20.8% tannins [51]. Tannins belong to cathodic corrosion inhibitors that can be used in a neutral pH environment [63].

Other chemical compounds in wood extractives that affect corrosion include nitrogen (N), phosphorus (P), sulphur (S) groups, and combinations with double or triple bonds [64]. Alkaloids are chemical compounds containing a nitrogen group. They are sometimes associated with a heterocyclic carbon group, and their presence in wood extractives is slight, such as taxols, xanthines, quinines, and others [65]. A natural material quinine can inhibit the corrosion of low carbon steel with an efficiency of up to 96% [66].

7. Construction failures

Wood species affect the corrosion rate of nails and screws used as connecting materials. The weight loss of screws mounted in *Ficus nervosa* wood was 6.91–7.23% [67], that in *Melaleuca cajuputi* wood was 5.96% [68], and that in *Castanopsis acuminatissima* wood was 6.89% [69].

When the wood is nailed, the structure of the wood is damaged, and the process of wood deterioration begins [70]. The wood weight loss due to screw installation on *Litsea roxburghii* wood was 16.31% [68], and that on *Castanopsis tunggurut* wood was 7.23% [69]. Threads on bolts cause more severe wood damage if the connection to the wood construction is damaged [71]. The nailing process, especially using an airgun nailing device at a speed of 30 m/s, causes friction of the cell walls, which can degrade lignin in the cell wall [70].

The weight loss of wood due to metal corrosion of nails and bolts as well as chemical damage to wood will cause a decrease in the mechanical properties of wood. The bearing strength of the screw also increases with an increase in the maximum compressive strength parallel to the wood grain [72]. Damage to the wood around a screw can result in damage to the joint due to holding the maximum grain parallel pressure from the screw [73].

8. Technical treatments

The treatment of wood and nails or bolts can prevent corrosion. Wood with a low moisture content dried by kiln-drying has a stronger screw/nail connection and lasts longer than fresh wood [74]. Wood with a moisture content below the EMC tends to have minimal or no corrosion [75].

Treatment of wood, such as the addition of preservatives, can cause changes in the corrosion rate when compared to untreated wood. Acetylated wood does not affect nail corrosion rate [76]. Wood preserved with DDAC (dodecyl dimethyl ammonium carbonate) has a higher corrosion rate than wood preserved with copper-based preservatives such as CCA, ACQ and CuAz [77]. Addition of PEG to wood can function as a corrosion inhibitor [78]. Some fire-retardants can trigger corrosion [79].

Bolted joints with slotted-in steel plates in round timber provided higher mechanical strength with a longer joint life [12]. Coating the surface of bolts and nails can reduce the corrosion rate [44]. The coating process acts as anodic protection in the corrosion inhibition process [50]. Extractives from a natural product containing C, N, O, S, or functional groups such as alkaloids, terpenes, carboxylic acids, polyphenols, quinine, and nicotine can be attached to metal surfaces to form a thin layer that can prevent corrosion [80].

Nails or bolts can be surface thermal diffusion galvanized to reduce corrosion in a more environmentally friendly manner [81]. Wetting and drying tests on galvanized nails did not significantly affect the corrosion rate of nails nailed into wood [82]. The galvanization process can use Zn phosphate, Fe phosphate, duralumin or aluminum bronze to form a metal alloy with high corrosion resistance [83]. By keeping the temperature low, the screw drilling process can inhibit the corrosion process [84].

Conclusion

The widespread utilization of wood in outdoor and indoor construction causes variations in the corrosion of nails and bolts used as wood connectors. The chemical elements of nails and bolts, such as iron, carbon, zinc, and several other chemical elements, play an important role. In comparison, the wood part that affects the corrosion rate is the wood extractives which comprise phenolic compounds, organic acids, and several other wood chemical compounds. The occurrence of corrosion processes and interactions with wood cause damage to wood and wood deterioration which can cause damage to wooden construction structures. Preventing corrosion and wood damage can be done by coating nails and bolts and improving wood quality, such as wood drying and addition of corrosion inhibitor additives.

Acknowledgment

All authors have the same contribution to this paper.

References

1. N. Viholainen, F. Franzini, K. Lahinen, A.Q. Nyrud, C. Widmark, H.F. Hoen and A. Toppinen, Citizen views on wood as a construction material: Results from seven european countries, *Can. J. For. Res.*, 2021, **51**, no. 5, 647–659. doi: [10.1139/cjfr-2020-0274](https://doi.org/10.1139/cjfr-2020-0274)
2. S. Cascone, F. Catania and G. Sciuto, Wooden Building Technology and Proposal for an Innovative Solution, In: *42nd IAHS WORLD CONGRESS*, 2018, 1–12.
3. M.K. Kuzman and P. Grošelj, Wood as a construction material: Comparison of different construction types for residential building using the analytic hierarchy process, *Wood Res.*, 2012, **57**, no. 4, 591–600.
4. E. Hurmekoski, How Can Wood Construction Reduce Environmental Degradation?, European Forest Institute, 2017, 12 p.
5. J. Hart and F. Pomponi, More timber in construction: Unanswered questions and future challenges, *Sustainability*, 2020, **12**, no. 8. doi: [10.3390/su12083473](https://doi.org/10.3390/su12083473)
6. O. Percin and O. Uzun, Screw Withdrawal Strength of Heat-Treated and Laminated Veneer Lumber Reinforced with Carbon and Glass Fibers, *BioResources*, 2022, **17**, no. 2, 2486–500. doi: [10.15376/biores.17.2.2486-2500](https://doi.org/10.15376/biores.17.2.2486-2500)
7. M. Riggio, J. Sandak and A. Sandak, Densified wooden nails for new timber assemblies and restoration works: A pilot research, *Constr. Build. Mater.*, 2016, **102**, 1084–1092. doi: [10.1016/j.conbuildmat.2015.06.045](https://doi.org/10.1016/j.conbuildmat.2015.06.045)
8. M. Sydor, Geometry of wood screws: a patent review, *Eur. J. Wood Wood Prod.*, 2019, **77**, no. 1, 93–103. doi: [10.1007/s00107-018-1362-4](https://doi.org/10.1007/s00107-018-1362-4)
9. N.M. Aljamali, N.M.B. Mohsin and N. Ali, Review on Corrosion and Rust Inhibition of Machines in Chemical Engineering Field, *Int. J. Thermodyn. Chem. Kinet.*, 2019, **5**, 1–10.
10. S.L. Zelinka, Corrosion of embedded metals in wood: An overview of recent research with implications for building moisture design, *ASHRAE Trans.*, 2013, **119**, 442–448.
11. M.N. Nguyen, R.H. Leicester, C.H. Wang and G.C. Foliente, Corrosion effects in the structural design of metal fasteners for timber construction, *Struct. Infrastruct. Eng.*, 2013, **9**, no. 3, 275–284. doi: [10.1080/15732479.2010.546416](https://doi.org/10.1080/15732479.2010.546416)
12. A. Lokaj and K. Klajmonova, Dowel Type Joints of Round Timber Exposed to Static and Cyclic Tension Forces, *Procedia Eng.*, 2015, **114**, 240–247. doi: [10.1016/j.proeng.2015.08.064](https://doi.org/10.1016/j.proeng.2015.08.064)
13. V.A. De Araujo, J. Cortez-Barbosa, M. Gava, J.N. Garcia, A.J.D. de Souza, A.F. Savi, E.A.M. Morales, J.C. Molina, J.S. Vasconcelos, A.L. Christoforo and F.A.R. Lahr, Classification of wooden housing building systems, *BioResources*, 2016, **11**, no. 3, 7889–7901. doi: [10.15376/biores.11.3.DeAraujo](https://doi.org/10.15376/biores.11.3.DeAraujo)
14. U.J. Cahyono, B. Setioko and T.W. Murtini, Transformation of form in the growth of modern Javanese house in Laweyan Surakarta, *J. Archit. Urban.*, 2017, **41**, no. 4, 288–295. doi: [10.3846/20297955.2017.1411848](https://doi.org/10.3846/20297955.2017.1411848)

15. Khairussa'diah and Y.P. Prihatmaji, Resisting Timber Joint Performance of Karo Wooden Building, *Wood Res. J.*, 2020, **10**, no. 1, 1–5. doi: [10.51850/wrj.2019.10.1.1-5](https://doi.org/10.51850/wrj.2019.10.1.1-5)
16. Yunitha and M. Guntur, Baruk, A Traditional House of Bidayuh in Borneo, Its Space Related to Structure. In: Proceedings of the International Conference of Heritage & Culture in Integrated Rural-Urban Context (HUNIAN 2019), 2020, 14–21. doi: [10.2991/aer.k.200729.003](https://doi.org/10.2991/aer.k.200729.003)
17. M. Guntur, K.R. Kurniawan and Yunitha, Baruk, A Traditional House of Bidayuh in Borneo, Its Space Related to Structure, In: 12th International Conference on Structural Analysis of Historical Constructions SAHC 2020, 2020, 1–12.
18. M. Mohammad, M. Popovski, C. Ni, M. Rezai, K. Below, R. Malczyk and J. Sherstobitoff, Design and Construction of Tall Wood Buildings: Input Data, Testing and Advanced Analysis, *WCTE 2014 - World Conf. Timber Eng.*, 2014, 1–12.
19. J. Bigelow, S. Lebow, C.A. Clausen, L. Greimann and T.J. Wipf, Preservation treatment for wood bridge application, *Transp. Res. Rec.*, 2009, no. 2108, 77–85.
20. S. Rashidyan, T.T. Ng and A. Maji, Exploratory Study of Nondestructive Parallel Seismic Testing Challenges in Estimating the Depth of Unknown Wood Bridge Foundations, *J. Perform. Constr. Facil.*, 2020, **34**, no. 3, 06020002. doi: [10.1061/\(ASCE\)CF.1943-5509.0001448](https://doi.org/10.1061/(ASCE)CF.1943-5509.0001448)
21. S. Sadiyo, I. Wahyudi, F.S. Yoresta, Nurhasanah and M. Sholihin, Analisis Kekuatan Sambungan Geser Ganda Enam Jenis Kayu Pada Berbagai Sesaran Menurut Diameter Dan Jumlah Baut, *Perennial*, 2012, **8**, no. 2, 52. doi: [10.24259/perennial.v8i2.215](https://doi.org/10.24259/perennial.v8i2.215)
22. W. Supriyati, T.A. Prayitno, S. Sumardi and S.N. Marsoem, KEARIFAN LOKAL PENGGUNAAN KAYU GELAM DALAM TANAH RAWA GAMBUT DI KALIMANTAN TENGAH (Local Wisdom of Utilization of Gelam Wood on Peat swamp Land of Central Kalimantan), *J. Manusia Lingkung*, 2015, **22**, no. 1, 94. doi: [10.22146/jml.18729](https://doi.org/10.22146/jml.18729)
23. Y.F. Arifin, S. Hamidah and Y.F. Arifin, The Analysis of Management and Timber Trade System of Gelam (*Melaleuca cajuputi*) From Peat Swamp Forest in South Kalimantan, *J. Wetl. Environ. Manag.*, 2016, **2**, no. 2, 79–83. doi: [10.20527/jwem.v2i2.40](https://doi.org/10.20527/jwem.v2i2.40)
24. W.A. Hayati, Erwin, N. Husien, S. Wahyuni, I.Y. Wardhani and A.S. Budi, Patterns of Iron Stain on Gelam Wood (*Melaleuca cajuputi* Powell), *Proc. Jt. Symp. Trop. Stud.*, 2021, **11**, 410–413. doi: [10.2991/absr.k.210408.067](https://doi.org/10.2991/absr.k.210408.067)
25. M. Duginske, *Introduction to Basic Cabinetmaking using Pocket-Screw Joinery*, 2005, 1–39.
26. J. Smardzewski and A. Majewski, Strength and durability of furniture drawers and doors, *Mater. Des.*, 2013, **51**, 61–66. doi: [10.1016/j.matdes.2013.03.101](https://doi.org/10.1016/j.matdes.2013.03.101)
27. D. Albright, V. Blouin, D. Harding, U. Heine, N. Huetten and D. Pastre, Sim[PLY]: Sustainable Construction with Prefabricated Plywood Componentry, *Procedia Environ. Sci.*, 2017, **38**, 760–764. doi: [10.1016/j.proenv.2017.03.159](https://doi.org/10.1016/j.proenv.2017.03.159)

-
28. C.F. da Silva, B. Stefanowski, D. Maskell, G.A. Ormondroyd, M.P. Ansell, A.C. Dengel and R. Ball, Improvement of indoor air quality by MDF panels containing walnut shells, *Build. Environ.*, 2017, **123**, 427–436. doi: [10.1016/j.buildenv.2017.07.015](https://doi.org/10.1016/j.buildenv.2017.07.015)
 29. S.L. Zelinka and D.R. Rammer, Corrosion Rates of Fasteners in Treated Wood Exposed to 100% Relative Humidity, *J. Mater. Civ. Eng.*, 2009, **21**, no. 12, 758–763. doi: [10.1061/\(ASCE\)0899-1561\(2009\)21:12\(758\)](https://doi.org/10.1061/(ASCE)0899-1561(2009)21:12(758))
 30. V. Krasinskyi, T. Jachowicz, L. Dulebova, I. Gajdos and R. Malinowski, The Manufacturing of Composite Materials in the Matrix of Modified Phenol–Formaldehyde Resins, *Adv. Sci. Technol. Res. J.*, 2021, **15**, no. 4, 267–272. doi: [10.12913/22998624/142288](https://doi.org/10.12913/22998624/142288)
 31. J. Di and H. Zuo, Experimental and reliability-based investigation on sheathing-to-framing joints under monotonic and cyclic loads, *Forests*, 2021, **12**, 8. doi: [10.3390/f12080995](https://doi.org/10.3390/f12080995)
 32. K. Frydryšek, Š. Michenková, L. Pleva, J. Koutecký, J. Fries, K.P. Dědková, R. Madeja, A. Trefil, P. Krpec, T. Halo, L. Hrabovsky, L. Bialy, R. Janco and J. Pokorny, Mechanics of Screw Joints Solved as Beams Placed in a Tangential Elastic Foundation, *Appl. Sci.*, 2021, **11**, no. 12, 5616. doi: [10.3390/app11125616](https://doi.org/10.3390/app11125616)
 33. C. Cristescu, D. Honfi, K. Sandberg, Y. Sandin, E. Shotton, M. Cramer, D. Ridley-Ellis, A. Harte, C. Ui Chulana, M. Risse, R. Ivanica, M. de Arana-Fernandes, M.G. Barbero, D. Llana, G. Íñiguez-González, B. Nasiri, M. Huges, Z. Krofl and S.J. Walsh, Design for deconstruction and reuse of timber structures – state of the art review, *ForestValue – InFutUReWood*, 2020, 1–92. doi: [10.23699/bh1w-zn97](https://doi.org/10.23699/bh1w-zn97)
 34. J. Jermer, B.-L. Andersson and J. Schalnat, Corrosion of fasteners in furfurylated wood: final report after 9 years exposure outdoors, *In: Proceedings IRG Annual Meeting*, 2017, Section 4 Processes and Properties.
 35. I.H. Lee, K. Kim and K.B. Shim, Evaluation of Bearing Strength of Self-Tapping Screws according to the Grain Direction of Domestic *Pinus densiflora*, *J. Korean Wood Sci. Technol.*, 2022, **50**, no. 1, 1–11. doi: [10.5658/WOOD.2022.50.1.1](https://doi.org/10.5658/WOOD.2022.50.1.1)
 36. Y. Liu, Y. Yao, F. Wang, H. Huang and Z. Que, Effect of arrangement distances on stiffness of shear-tension mode in timber-to-timber connections with inclined screws, *Constr. Build. Mater.*, 2022, **314**, 125592. doi: [10.1016/j.conbuildmat.2021.125592](https://doi.org/10.1016/j.conbuildmat.2021.125592)
 37. R. Jockwer, D. Caprio and A. Jorissen, Evaluation of parameters influencing the load-deformation behaviour of connections with laterally loaded dowel-type fasteners, *Wood Mater. Sci. Eng.*, 2022, **17**, no. 1, 6–19. doi: [10.1080/17480272.2021.1955297](https://doi.org/10.1080/17480272.2021.1955297)
 38. Y.A. Pranata, A. Kristianto and O. Pattipawaej, Beam-Column Timber Joint Connection Behavior Due to Nail and Modified-Washer Reinforcement Tests, *Wood Res. J.*, 2020, **10**, no. 1, 6–10. doi: [10.51850/wrj.2019.10.1.6-10](https://doi.org/10.51850/wrj.2019.10.1.6-10)
 39. Y. Zhang, M.L. Nehdi, X. Gao and L.V. Zhang, Flexural performance of novel nail-cross-laminated timber composite panels, *Appl. Sci.*, 2020, **10**, no. 17, 5983. doi: [10.3390/app10175983](https://doi.org/10.3390/app10175983)

-
40. A. Taguchi, T. Kitami, S. Akamaru and T. Abe, Homogeneous surface coating of bolts, nuts, and screws by barrel-sputtering technique, *Surf. Coat. Technol.*, 2007, **201**, no. 24, 9512–9517. doi: [10.1016/j.surfcoat.2007.04.019](https://doi.org/10.1016/j.surfcoat.2007.04.019)
 41. Y. Feng, H. Tang and P. Shu, Failure Analysis of Engine Crankcast Bolts Treated by Alodine Anodic Technology, In: *International Conference on Intelligent Control and Computer Application (ICCA 2016)*, 2016, 327–330. doi: [10.2991/icca-16.2016.78](https://doi.org/10.2991/icca-16.2016.78)
 42. A. Čereška, A. Podvieszko and E.K. Zavadskas, Assessment of different metal screw joint parameters by using multiple criteria analysis methods, *Metals*, 2018, **8**, no. 5, 1–16. doi: [10.3390/met8050318](https://doi.org/10.3390/met8050318)
 43. G. Langelandsvik, T. Furu, O. Reiso and H.J. Roven, Effects of iron precipitation and novel metal screw extrusion on electrical conductivity and properties of AA1370 aluminum, *Mater. Sci. Eng.: B*, 2020, **254**, 114505. doi: [10.1016/j.mseb.2020.114505](https://doi.org/10.1016/j.mseb.2020.114505)
 44. J. Votava, Anticorrosion protection of strength bolts, *Acta Univ. Agric. Silvic. Mendelianae Brun.*, 2012, **60**, no. 1, 181–188. doi: [10.11118/actaun201260010181](https://doi.org/10.11118/actaun201260010181)
 45. E. Figueiredo, M. Araujo, R. Silva, J. Senna-Martinez and J. Ines Vaz, Characterisation of Late Bronze Age large size shield nails by EDXRF, micro-EDXRF and X-ray digital radiography, *Appl. Radiat. Isot.*, 2011, **69**, 1205–1211. doi: [10.1016/j.apradiso.2011.04.027](https://doi.org/10.1016/j.apradiso.2011.04.027)
 46. R. Miranda, Analisis Laju Korosi Pada Logam Melalui Proses Dipcoating Larutan, *J. Hadron*, 2020, **2**, no. 01, 29–33. doi: [10.33059/jh.v2i1.2733](https://doi.org/10.33059/jh.v2i1.2733)
 47. R. Gorejová, I. Šišoláková, P. Cipa, R. Džunda, T. Sopčák, A. Oriňak and R. Orinakova, Corrosion behavior of Zn, Fe and Fe-Zn powder materials prepared via uniaxial compression, *Materials*, 2021, **14**, no. 17, 4983. doi: [10.3390/ma14174983](https://doi.org/10.3390/ma14174983)
 48. N.S. Syafei, D. Hidayat, Emlliano and L. Men, Events of corrosion phenomena on carbon steel pipes in environment of sea water and ammonia solutions due to the presence of sweet gas, *EKSAKTA: Berkala Ilmiah Bidang MIPA*, 2019, **20**, no. 1, 86–99. doi: [10.24036/eksakta/vol20-iss1/178](https://doi.org/10.24036/eksakta/vol20-iss1/178)
 49. F. Ma, Q. Zeng, X. Lu, T. Wu, X. Lu, T. Zhang and X. Feng, Electrochemical study of stainless steel anchor bolt corrosion initiation in corrosive underground water, *Processes*, 2021, **9**, no. 9, 1–14. doi: [10.3390/pr9091553](https://doi.org/10.3390/pr9091553)
 50. H. Ameen, K.S. Hassan and B.R. Mohameed, The effect of electroplating of Cr and Sn on corrosion resistance of low carbon steel (CK15), *Am. J. Sci. Ind. Res.*, 2010, **1**, no. 3, 565–572. doi: [10.5251/ajsir.2010.1.3.565.572](https://doi.org/10.5251/ajsir.2010.1.3.565.572)
 51. S.Y. Shubkin, S.S. Buneev and V.L. Zakharov, Comparative content of biologically active substances in wood species of the north of the forest steppe on the example of Lipetsk region, *IOP Conf. Ser.: Earth Environ. Sci.*, 2021, **677**, no. 2, 022018. doi: [10.1088/1755-1315/677/2/022018](https://doi.org/10.1088/1755-1315/677/2/022018)
 52. S.L. Zelinka, D.R. Rammer and D.S. Stone, Corrosion of metals in contact with treated wood: Developing test methods, *NACE – Int. Corros. Conf. Ser.*, 2008, 08403, 1–9.

-
53. M.M.A. Mansour, S.A.E.K.M. Hamed, M.Z.M. Salem and H.M. Ali, Illustration of the effects of five fungi on acacia salignawood organic acids and ultrastructure alterations in wood cell walls by HPLC and TEM examinations, *Appl. Sci.*, 2020, **10**, no. 8, 1–14. doi: [10.3390/app10082886](https://doi.org/10.3390/app10082886)
54. S.L. Zelinka and D.S. Stone, The effect of tannins and pH on the corrosion of steel in wood extracts, *Mater. Corros.*, 2011, **62**, no. 8, 739–744. doi: [10.1002/maco.201005845](https://doi.org/10.1002/maco.201005845)
55. S.E. Orozco, R.H. Bischof, S. Barbini, D. Sriranganadane, K. Fackler and A. Potthast, Fate of Lipophilic Wood Extractives in Oxygen-Based Cellulose Bleaching, *ACS Sustainable Chem. Eng.*, 2021, **9**, no. 13, 4840–4849. doi: [10.1021/acssuschemeng.1c00109](https://doi.org/10.1021/acssuschemeng.1c00109)
56. M. Lehr, M. Miltner and A. Friedl, Removal of wood extractives as pulp (pre-)treatment: a technological review, *SN Appl. Sci.*, 2021, **3**, 886. doi: [10.1007/s42452-021-04873-1](https://doi.org/10.1007/s42452-021-04873-1)
57. M. Krishnan, H. Subramanian, H.U. Dahms, V. Sivanandham, P. Seeni, S. Gopalan, A. Mahalingam and A.J. Rathinam, Biogenic corrosion inhibitor on mild steel protection in concentrated HCl medium, *Sci. Rep.*, 2018, **8**, no. 1, 1–16. doi: [10.1038/s41598-018-20718-1](https://doi.org/10.1038/s41598-018-20718-1)
58. M.S. Nascimento, A.L.B.D. Santana, C.A. Maranhao, L.S. Oliveira and L. Bieber, Phenolic Extractives and Natural Resistance of Wood, *In: Biodegradation - Life of Science*, 2013, 349–369.
59. P. Singh, V. Srivastava and M.A. Quraishi, Novel quinoline derivatives as green corrosion inhibitors for mild steel in acidic medium: Electrochemical, SEM, AFM, and XPS studies, *J. Mol. Liq.*, 2016, **216**, 164–173. doi: [10.1016/j.molliq.2015.12.086](https://doi.org/10.1016/j.molliq.2015.12.086)
60. A. Rajendran, Isolation, characterization, pharmacological and corrosion inhibition studies of flavonoids obtained from Nerium oleander and Tecoma stans, *Int. J. PharmTech. Res.*, 2011, **3**, no. 2, 1005–1013.
61. J.V. Nardeli, C.S. Fugivara, M. Taryba, E.R.P. Pinto, M.F. Montemor and A.V. Benedetti, Tannin: A natural corrosion inhibitor for aluminum alloys, *Prog. Org. Coat.*, 2019, **135**, 368–381. doi: [10.1016/j.porgcoat.2019.05.035](https://doi.org/10.1016/j.porgcoat.2019.05.035)
62. M. Dargahi, A.L.J. Olsson, N. Tufenkji and R. Gaudreault, Green technology: Tannin-based corrosion inhibitor for protection of mild steel, *Corrosion*, 2015, **71**, no. 11, 1321–1329. doi: [10.5006/1777](https://doi.org/10.5006/1777)
63. V. Sastri, *Green Corrosion Inhibitors (Theory and Practice)*, 2011, 1–305.
64. N. Patni, S. Agarwal and P. Shah, Greener Approach towards Corrosion Inhibition. *Chin. J. Eng.*, 2013, 784186, 1–10. doi: [10.1155/2013/784186](https://doi.org/10.1155/2013/784186)
65. I. Desgagné-Penix, Distribution of alkaloids in woody plants, *Plant Sci. Today*, 2017, **4**, no. 3, 137–142. doi: [10.14719/pst.2017.4.3.320](https://doi.org/10.14719/pst.2017.4.3.320)
66. M.I. Awad, Eco friendly corrosion inhibitors: Inhibitive action of quinine for corrosion of low carbon steel in 1 M HCl, *J. Appl. Electrochem.*, 2006, **36**, no. 10, 1163–1168. doi: [10.1007/s10800-006-9204-1](https://doi.org/10.1007/s10800-006-9204-1)

-
67. S. Suprapti and D. Djarwanto, Uji Pelapukan Pada Lima Jenis Kayu Yang Dipasang Sekrup Logam, *J. Penelit. Has. Hutan.*, 2015, **33**, no. 4, 365–376. doi: [10.20886/jphh.2015.33.4.365-376](https://doi.org/10.20886/jphh.2015.33.4.365-376)
68. D. Djarwanto, Sifat Pengkaratan Lima Jenis Kayu yang Disimpan di Tempat Terbuka Terhadap Besi, *J. Penelit. Has. Hutan.*, 2011, **29**, no. 2, 104–114. doi: [10.20886/jphh.2011.29.2.104-114](https://doi.org/10.20886/jphh.2011.29.2.104-114)
69. D. Djarwanto, Sifat Pengkaratan Besi pada Sebelas Jenis Kayu, *J. Penelit. Has. Hutan.*, 2010, **28**, no. 3, 255–262. doi: [10.20886/jphh.2010.28.3.255-262](https://doi.org/10.20886/jphh.2010.28.3.255-262)
70. H. Korte, G. Koch, K.C. Krause, T. Koddenberg and S. Siemers, Wood nails to fix softwoods: characterization of structural deformation and lignin modification, *Eur. J. Wood Wood Prod.*, 2018, **76**, no. 3, 979–988. doi: [10.1007/s00107-018-1288-x](https://doi.org/10.1007/s00107-018-1288-x)
71. Z. Huang, S.Q. Shi and L. Cai, Experimental analysis on strength and failure modes of wood beam-column connections, *Front. Struct. Civ. Eng.*, 2014, **8**, no. 3, 260–269. doi: [10.1007/s11709-014-0261-y](https://doi.org/10.1007/s11709-014-0261-y)
72. S. Sadiyo, N. Elsa and S. Pratiwi, Nilai Kekuatan Tumpu Baut pada Empat Jenis Kayu Rakyat Indonesia, *Jurnal Teknik Sipil*, 2017, **24**, no. 2, 153–158. doi: [10.5614/jts.2017.24.2.6](https://doi.org/10.5614/jts.2017.24.2.6)
73. K. Sawata, Strength of bolted timber joints subjected to lateral force, *J. Wood Sci.*, 2015, **61**, no. 3, 221–229. doi: [10.1007/s10086-015-1469-8](https://doi.org/10.1007/s10086-015-1469-8)
74. M. Harada, Y. Hayashi, T. Hayashi, M. Karube and T. Ohgama, Effect of moisture content of members on mechanical properties of timber joints, *J Wood Sci.*, 2005, **51**, no. 3, 282–285. doi: [10.1007/s10086-004-0656-9](https://doi.org/10.1007/s10086-004-0656-9)
75. H.R. Trechsel and M.T. Bomberg, *Moisture Control in Buildings: The Key Factor in Mold Prevention – 2nd Edition*, Library of Congress Cataloging-in-Publication Data, 2009.
76. S.L. Zelinka and L. Passarini, Corrosion of metal fasteners embedded in acetylated and untreated wood at different moisture contents, *Wood Mater. Sci. Eng.*, 2020, **15**, no. 4, 182–189. doi: [10.1080/17480272.2018.1544171](https://doi.org/10.1080/17480272.2018.1544171)
77. S.L. Zelinka, D.R. Rammer and D.S. Stone, Evaluating the corrosiveness of southern pine treated with several wood preservatives using electrochemical techniques, *NACE Int.*, 2009, (January 2014).
78. M. Broda and C.A.S. Hill, Conservation of waterlogged wood – past, present and future perspectives, *Forests*, 2021, **12**, no. 9, 1–55. doi: [10.3390/f12091193](https://doi.org/10.3390/f12091193)
79. D. Sandberg, Additives in wood products – today and future development, *Environmental Footprints and Eco-Design of Products and Processes*, 2016, 105–172. doi: [10.1007/978-981-10-0655-5_4](https://doi.org/10.1007/978-981-10-0655-5_4)
80. Inamuddin, M.I. Ahamed, M. Luqman and T. Atalhi, *Sustainable corrosion inhibitors*, 2021, 1–225.
81. A. Vallien, B. Solem and P. Wernstedt, *Applying Thermal Diffusion Galvanization on Wood Screws*, 2016.

-
82. L. Yermán, L.M. Ottenhaus, C. Montoya and J.J. Morrell, Effect of repeated wetting and drying on withdrawal capacity and corrosion of nails in treated and untreated timber, *Constr. Build. Mater.*, 2021, **284**, 1–9. doi: [10.1016/j.conbuildmat.2021.122878](https://doi.org/10.1016/j.conbuildmat.2021.122878)
83. D.P. Burduhos-Nergis, D.D. Burduhos-Nergis and C. Bejinariu, Galvanic corrosion behaviour of different types of coatings used in safety systems manufacturing, *Coatings*, 2021, **11**, no. 12, 1542. doi: [10.3390/coatings11121542](https://doi.org/10.3390/coatings11121542)
84. K. Roy, H.H. Lau, Z. Fang, R. Masood, T.C.H. Ting, J.B.P. Lim and V.C.C. Lee, Effects of corrosion on the strength of self-drilling screw connections in cold-formed steel structures – Experiments and finite element modeling, *Structures*, 2022, **36**, 1080–1096. doi: [10.1016/j.istruc.2021.12.052](https://doi.org/10.1016/j.istruc.2021.12.052)

